



Product information | TECHNICAL DATA SHEET

GREY FILLER PRIMER

400 ml, 11 Oz, 318 g.

GENERAL DESCRIPTION

Highly thick primer paint "Filler Primer" monocomponent manufactured with a modified nitro alkyd resins that allow for excellent recoatability.d.Primer filler can be used on primers, polyester putty, or directly on sanded down panels to obtain a filling and leveling effect on the surface.

CARACTERÍSTICAS

- Fast drying.
- High filling power.
- Easy to sand down.
- It does not contain lead or other heavy metals.
- Easy to apply and recoat.

APLICACIONES

Primer filler can be used on primers, polyester putty or directly on sanded down panels.

- Industry

- Automotive industry

INSTRUCCIONES DE USO

- For professional use only.
- Shake the aerosol well before using, approximately for one minute after hearing the sound of the mixer.
- For best results apply in thin layers. Three thin layers are always better than one thick one, and may be repainted within 20 minutes with the same paint.
- Do not apply on thermoplastic acrylic enamels. For panel: degreases and removes rust. On 2C Polyester putty: apply directly on to sanded down surface
- Turn the aerosol upside down to clean out the valve after use. If te nozzle becomes blocked replace it with a new one.
- Never apply to equipment that is plugged in and use in well ventilated areas.
- Request safety datasheets.

CARACTERÍSTICAS FÍSICAS

Binder type:	Nitrosintético
Color:	Grey
Shine 60°:	<10%
Dry to the touch (ASTM D-1640 ISO 1517):	10'
Total drying (ASTM D-1640 ISO 1517):	2 h
Theorical yield (continuous painting):	2 m²
Thinner:	Butyl Acetate
Product life:	(Well Stored) 5 Years
Recoating:	After 10'
Condition for application:	Tº environment min. 8°C
	T° surface min.5-50°C
	Humidity Max. 85% R.H.P

Montana Colors, S.L. P.I. Clot del Tufau - 08295 Sant Vicenç de Castellet BARCELONA

T.: +34 938 332 787 - montana@montanacolors.com - www.montanacolors.com

IMAGE



LID

Protects the valve and the nozzle.

LABEL **CAP SYSTEM**





PACKAGING

Nominal capacity 400 ml. Heat resistanve of packaging: <50°C Propellant: GLP - HC C3-C4 VOC's: 655g/L

Box (6 units)

205 X 140 X 200 mm.













^{*} Adherence tests were performed on steel.